

byk®



BYK 3015 WATERTECH FLEX UV

Cement and Polymer Based, Two Component, Resistant to UV, White, Highly Elastic Waterproofing Material

BYK 3015 WATERTECH FLEX UV, is cement and polymer dispersion based, two component, Resistant to UV, white, highly elastic waterproofing material designed for all kinds of reinforced concrete surface and cement based screeds.

FIELDS OF APPLICATION

- Inside - outdoors, on the positive side where the water comes vertically and horizontally,
- Pools and water tanks,
- Bathroom, WC etc. in all wet volumes,
- On terraces, balcony and roofs
- On foundation, curtain and retaining walls,
- In flowerpot insulation,
- Used in drinking water tanks,
- Olympic swimming pools and thermal pools,
- In cold weather storages walls and upholstery

ADVANTAGES

- Resistant to UV,
- Fully elastic and water impermeable, Easy to prepare and apply,
- Can be applied with brush or spraying machine, Long working time,
- Excellent adhesion and crack bridging,
- Form a water impermeable layer under the screed and ceramic,
- Creates a joint less, seamless, permanent, waterproof coating,
- Resistant to chemical and salt solutions in the ground,
- Can be used in motion and vibrating areas, Resistant to freeze-thaw effect,

TECHNICAL FEATURES

Structure of the material	A component	Special cement, mineral filling, polymer
	B component	Liquid polymer dispersion
Density		1,70 kg/l
Color		White
Bonding Strength		$\geq 1,50$ N/mm ²
Resistance To Water In Pressure		7 bar (Positive)
Adhesion Strength After Heat Ageing		$\geq 1,00$ N/mm ²
Adhesion Strength After Contact With Limy Water		$\geq 0,50$ N/mm ²
Adhesion Strength After Contact With Chlorinat Water		$\geq 0,50$ N/mm ²
Crack Bridging		$\geq 0,75$ mm
Application Surface Temperature		+5°C / +35°C
Service Temperature		-20°C / +80°C
Use time of the mixing		2 hours
Working Time	Mechanical Strength after	2 days
	Water Impermeability	7 days
Can be coated	Screed or Ceramic after	3 days

The values above are given for +23°C and 50% relative humidity. While higher temperatures shorten the period, lower temperatures extend it

APPLICATION PROCEDURE

Preparation of the Substrate

The surface to be applied must be solid, free from any oil, grease, rust, paraffin, paint, bitumen residues that will prevent adhesion to the surface and all loose parts must be cleaned. Iron and wooden wedges on the surface should be removed and active water leaks, if any, should be repaired with **BYK 1102 PLUG** and the gaps, uneven surfaces and corner edges (chamfer making at least 4 cm) should be repaired with **BYK 4014 REPAIR** mortars. The surface should be wetted before application. If waterproofing material loses its water immediately and takes a matte appearance during application, it is understood that the surface is not wetted sufficiently or the product dries quickly due to weather conditions. In cases where such air is hot or the materials are in the wind, the water through 10% of **BYK 3015 WATERTECH FLEX UV B** component is added to the mixed material for the first layer.

Mixing

The 1/2 of the BYK 3015 **WATERTECH FLEX UV B** component is poured into a clean mixing chamber. While the BYK 3015 **WATERTECH FLEX UV A** component is slowly added, it is mixed for about 3-5 minutes with an electric mixer of 400-600 rpm and the appropriate mixer. The mixture coming to the paste consistency is allowed to rest for 2 minutes, then the remaining B component is added and mixed for 1-2 minutes to prepare for application.



www.bykbinyapi.com

BYK 3015 WATERTech FLEX UV

Cement and Polymer Based, Two Component, Resistant to UV, White, Highly Elastic Waterproofing Material

Application

The prepared **BYK 3015 WATERTech FLEX UV** mixture is applied in two or three layers with the help of an insulating brush. The direction of brush application on each floor should be perpendicular to each other. Waiting time between layers varies according to ambient conditions.

Consumption

1st layer; 1,00 kg/m²
2nd layer; 1,00 kg/m²
3rd layer; 1,00 kg/m²

Package


30 kg set / A component 20 kg Kraft bag. B component 10 kg Bucket.

Cleaning of Application Tools

Tools and equipment used after application should be cleaned with water.

Watch Points

- In the application of **BYK 3015 WATERTech FLEX UV**, if the ambient and surface temperature is below +5°C or above +35°C, suitable temperatures should be expected. Application should not be made in extremely hot, rainy or windy weather.
- **BYK 3015 WATERTech FLEX UV** applied at +23°C gains mechanical strength after 2 days, becomes waterproof after 7 days and reaches its final strength after 28 days.
- In exterior surface applications, the surface should be protected from sun, wind, rain or frost for the first 24 hours.
- Working and reaction times of cement and acrylic based systems are affected by ambient and ground temperature and relative humidity in the air. At low temperatures, the reaction slows down, which increases pot life and working time. High temperatures accelerate the reaction and the times mentioned above are shortened accordingly.
- In order for the material to complete its curing, the floor temperature and ambient temperature to be applied must not fall below the minimum allowed value. In application, wet film thickness should not exceed 1,30 mm in one layer.



Shelf Life

Shelf life is 12 months from the date of production when stored properly at + 5 ° C to + 30 ° C, room temperature, away from direct sunlight. **BYK 2015 WATERTech FLEX B** component freezes at temperatures below 0 ° C. Opened packages should be kept tightly closed in suitable storage conditions and used within one week.

Storage

The product should be stored in its original package, in a cool and dry place protected from frost. For short term storage, maximum 2 pallets should be placed on top of each other and the shipment should be made on a 'first come, first go' basis. Pallets should not be placed on top of each other during long term storage.

Health and Safety Precautions

It is dangerous to approach the application sites with fire. Fresh air should be circulated in the storage and the application sites. During the application, a protective apparel, protective gloves, goggles and masks which comply with the Occupational Health and Safety Rules should be used. Due to the irritation effect of the uncured materials, the mixture should not come into contact with skin and eyes; in case of a contact, the affected area should be washed with plenty of water and soap; in case of swallowing, a physician should be consulted immediately. No food or beverages should be brought to the application area. The product should be stored and kept out of reach of children.

Disclaimer

The technical information given in this publication is based on the present state of our best scientific and practical knowledge. **BYK Binyapı Co.** is only responsible for the quality of the product. **BYK Binyapı Co.** is not responsible for results that may occur because the product is used other than advised and/or out of instructions regarding the place and the method of use. This technical form is valid only till a new version is implemented and nullifies the old ones.